

FLEXO® PRISMIX

RANDOM CAMOUFLAGE • DUAL-COLORED MONOFILAMENT

EVEN MORE COLOR POSSIBILITIES

Prismix (PTD) utilizes a cutting-edge dual-colored monofilament to produce never before possible color combinations. This new technology creates an incredible random camouflage in our exclusive new mix series of products. Be sure to utilize Prismix on your next adventure for the best braided camo you have ever seen, or not seen!

SIZING CHART


Nominal Size	Part #	Min Expansion	Max Expansion	*Put-Ups		Available Colors	Lbs/100'
				M	L		
1/8"	PTD0.13	3/32"	1/4"	225'	1,000'	2	0.20
1/4"	PTD0.25	1/8"	7/16"	200'	1,000'	2	0.30
3/8"	PTD0.38	3/16"	1/2"	125'	500'	2	0.57
1/2"	PTD0.50	1/4"	3/4"	100'	500'	2	0.77
5/8"	PTD0.63	3/8"	1"	100'	500'	2	0.95
3/4"	PTD0.75	1/2"	1 1/4"	75'	250'	2	1.20
1"	PTD1.00	5/8"	1 5/8"	65'	250'	2	1.34
1 1/4"	PTD1.25	3/4"	1 3/4"	50'	250'	2	1.60
1 1/2"	PTD1.50	1"	2 1/8"	40'	200'	2	1.96
1 3/4"	PTD1.75	1 1/4"	2 1/4"	30'	200'	2	2.45

*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool

FEATURES

Material	Polyethylene Terephthalate
Grade	PTD
Monofilament Diameter	.010"
Drawing Number	TF001PET-WD
Cutting	Hot Knife

COLORS



Expedition Mix (EM) and Trail Mix (TM)

CERTIFICATIONS



ABRASION

Abrasion Resistance	HIGH
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	77°F
Humidity	72%
Two Broken Filaments	300 Test Cycles
Approx. 6 Broken Filaments	500 Test Cycles
Material Destroyed	1,150 Test Cycles
Pre-Test Weight	4,547.4 mg
Post-Test Weight	4,133.9 mg
Test End Loss Of Mass Point Of Destruction	413.5 mg

PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	.010"
Flammability Rating	UL94
Recommended Cutting	Hot KnifeK
Colors	2
Wall Thickness	.025"
Tensile Strength (Yarn) (ASTM D-2256 Lbs)	7.5
Specific Gravity (ASTM D-792)	1.38
Moisture Absorption % (ASTM D-570)	.1-.2
Hard Vacuum Data (ASTM E-595 at 10-5 torr)	
TML	.19
CVCM	.00
WVR	.16
Smoke D-Max (ASTM E-662)	56
Outgassing	Medium
Oxygen Index (ASTM D-2863)	21

FLAMMABILITY

Rating	UL94
--------	------

OPERATING TEMPERATURES

Melt Point (ASTM D-2117)	482°F / 250°C
Maximum Continuous (Mil-I-23053)	257°F / 125°C
Minimum Continuous (Mil-I-23053)	-94°F / -70°C

CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected 4=More Affected 5=Severely Affected

Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water (O-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	1
Lube Oil (MIL-L-7808)	1
De-Icing Fluid (MIL-A-8243)	1
Strong Acids	3
Strong Oxidants	2
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus (ASTM G-21)	1
Halogen Free	Yes
RoHS	Yes
SVHC	None