

# SHRINKFLEX® 2:1 FABRIC SHRINKS TO 1/2 ITS ORIGINAL DIAMETER • HIGHLY FLEXIBLE EXCELLENT CHEMICAL RESISTANCE • MECHANICAL ABRASION PROTECTION

2:1 Fabric Heatshrink tubing, a unique mixture of Polyolefin and Polyester yarns which shrinks to ½ its original diameter, is the ideal way to form the only shrinkable fabric of its kind. The woven construction makes this product extremely flexible and resistant to trapping water, heat and humidity. Provides outstanding abrasion, chafing and cutting protection, even at high temperatures. Shrinkflex<sup>®</sup> Fabric tubing, designed primarily to provide mechanical abrasion protection for components such as rubber hoses, plastic pipes, and harness wiring bundles. Also suitable for other applications, such as noise and rattle suppression.

## **SIZING CHART**

Nominal	Part #	Unshrunk Diameter /mm	Shrunk Diameter /mm	*Put-Ups		Available	Lbs/
Size				М	L	Colors	100'
1⁄2"	H2F0.48BK	12	6	25'	100'	1	1.15
3⁄4"	H2F0.79BK	20	10	25'	100'	1	1.61
1 <sup>3</sup> / <sub>16</sub> "	H2F1.18BK	30	15	25'	100'	1	2.13
1½"	H2F1.58BK	40	20	25'	100'	1	2.66
2"	H2F1.97BK	50	25	25'	100'	1	3.44
2¾"	H2F2.36BK	60	30	25'	100'	1	4.11
2¾"	H2F2.75BK	70	35	25'	100'	1	4.69

\*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool



## FEATURES

Material	Polyolefin/Polyester
Grade	H2F
Monofilament Diameter	NA
Drawing Number	TF001H2F-WD
Cutting	Scissors



Black (BK)

## CERTIFICATIONS

**FL** () VW-1



**HEATSHRINK TUBING** 

Technical Data Sheet





#### **CHEMICAL RESISTANCE**

Lubricating Oil	High
Antifreeze (50% Ethylene Glycol)	High
Brake Fluid	High
Engine Oil	High
Unleaded Gasoline	High
Diesel Fluid	High
Hydraulic Fluid	High
Mineral Hydraulic Fluid	High
Battery Acid	High
Water	High

### FLAMMABILITY

Rating	Non-Flame Retardant

## **OPERATING TEMPERATURES**

Shrinks	275°F / 135°C
Maximum Continuous (Mil-I-23053)	275°F / 135°C
Minimum Continuous (Mil-I-23053)	-40°F / -40°C

## **PHYSICAL PROPERTIES**

Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	Non-Flame Retardant
Recommended Cutting	Scissors
Colors	1
Wall Type	Single
Pliancy	Very Flexible
Abrasion Resistance	High



## HOW-TO

Measure the Shrinkflex<sup>®</sup> tubing to length and cut with a scissor. The thickness of your bundle, as well as the desired final appearance, will determine the length of the tubing you cut. Generally, a piece 1<sup>1</sup>/<sub>2</sub>" - 2" long will accommodate almost any need. Single wires, or smaller bundles, require shorter pieces.



Slip the Shrinkflex<sup>®</sup> tubing over the bundle and position it so that both the sleeved and unsleeved portions are sufficiently covered. Notice the small pieces of tubing installed on single wires as part of a color coding system. If your project requires multiple operations, always work up from the smallest to the largest bundle.



Gently apply heat to Shrinkflex<sup>®</sup> tubing from a heat gun, hair dryer or torch with an appropriate attachment. Keep the heat source far enough away so that hot metal or direct flame does not come in contact with the tubing, wires or sleeving. Move the heat around the bundle to prevent damaging the sleeving and to ensure that all areas of the tubing have been shrunk. Once cooled, your installation is complete.

#### www.TECHFLEX.com

104 Demarest Road • Sparta, NJ 07871 • 1 (833) SLEEVING • (973) 300-9242 • fax: (973) 300-9409

© 2023 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden. Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.