



INSULTHERM® HEADER WRAP

VERMICULITE COATED FIBERGLASS WRAP · WITHSTANDS HEAT UP TO 1,200°F INCREASES HORSEPOWER & IMPROVES FUEL MILEAGE

Insultherm® Header Wrap is extremely high temperature resistant. Commonly used for the headers and exhaust. Manufactured from texturized fiberglass yarns and woven into a strong and flexible wrap with vermiculite coating. It reduces under-hood temp. up to 70%, increases horsepower and fuel efficiency. Header Wrap works by holding heat within the header, which creates a better exhaust flow. This allows easy removal of spent gases and creates more airflow to the engine.

SIZING CHART

Wall Thickness	Part #	Width	*Put-Ups			Available Colors	Lbs/100'
			S	M	L		
1/16"	HFN1.00	1"	25'	50'	100'	2	1.50
1/16"	HFN2.00	2"	25'	50'	100'	2	3.05

*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool

FEATURES

Material	Fiberglass
Grade	HFN
Wall Thickness	.0625"
Drawing Number	TF001HFN-WD
Cutting	Scissors

COLORS



Natural (NT), Black (BK)

CERTIFICATIONS





ABRASION

Abrasion Resistance	MEDIUM
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	75°F
Humidity	65%
Material Beginning To Wear Through In One Spot	400 Test Cycles
Material Destroyed	500 Test Cycles
Pre-Test Weight	13,162.7 mg
Post-Test Weight	11,614.3 mg
Test End Loss Of Mass Point Of Destruction	1,548.4 mg

PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	Non Flammable
Recommended Cutting	Scissors
Colors	2
Wall Thickness	.625"
Tensile Strength (Yarn) (ASTM D-2256 Lbs)	NA
Specific Gravity (ASTM D-792)	2.6
Moisture Absorption % (ASTM D-570)	NA
Hard Vacuum Data (ASTM E-595 at 10-5 torr)	NA
TML	NA
CVCN	NA
WVR	NA
Smoke D-Max (ASTM E-662)	NA
Outgassing	NA
Oxygen Index (ASTM D-2863)	NA

FLAMMABILITY

Rating	Non Flammable
--------	---------------

OPERATING TEMPERATURES

Melt Point (ASTM D-2117)	2,048°F / 1,120°C
Maximum Continuous (Mil-I-23053)	1,200°F / 649°C
Minimum Continuous (Mil-I-23053)	-70°F / -57°C

CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected 4=More Affected 5=Severely Affected

Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	1
Weak Bases	1
Salts	1
Strong Bases	1
Salt Water (O-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	1
Lube Oil (MIL-L-7808)	1
De-Icing Fluid (MIL-A-8243)	1
Strong Acids	2
Strong Oxidants	2
Esters/Ketones	1
UV Light	2
Petroleum	1
Fungus (ASTM G-21)	1
Halogen Free	Yes
RoHS	Yes
SVHC	NA