



## **DRAGON SLEEVE®** **LIGHTWEIGHT · FLAME RESISTANT · RESISTS SPARKS** **DOUBLE WALL CONSTRUCTION · TEAR RESISTANT**

Techflex® Dragon Sleeve® (DGN) is a truly non flammable product created for use in the most extreme environments. If your application comes in contact with flames, molten metal, sparks or any variety of high temperature hazard Dragon products are available to take the abuse. Industries like motorsports, welding, fabrication, and fire safety will appreciate the versatility of Dragon Sleeve®. The high flexibility braided construction is a one of a kind solution for covering hoses and wires with a fire prevention jacket. When compared to other “non-flammable” fibers such as para-aramids Dragon fiber maintains 100% of its strength longer and at higher temperatures. Dragon Sleeve® is available in 8 standard sizes.

### SIZING CHART

Nominal Size	Part #	Min Expansion	Max Expansion	Wall Thickness	*Put-Ups		Available Colors	Lbs/100'
					M	L		
1/8"	DGN0.13BK	1/16"	3/16"	.020"	225'	500'	1	0.20
1/4"	DGN0.25BK	1/8"	5/16"	.021"	200'	500'	1	0.42
3/8"	DGN0.38BK	3/16"	9/16"	.022"	125'	500'	1	0.61
1/2"	DGN0.50BK	5/16"	7/8"	.020"	100'	500'	1	0.80
3/4"	DGN0.75BK	3/8"	1"	.021"	75'	250'	1	1.24
1 1/4"	DGN1.25BK	5/8"	1 3/4"	.027"	50'	250'	1	2.03
1 3/4"	DGN1.75BK	3/4"	2 1/8"	.021"	50'	200'	1	2.57
2"	DGN2.00BK	1"	2 3/4"	.021"	50'	200'	1	3.17

\*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool



### FEATURES

Material	Carbon Fiber
Grade	DGN
Wall Thickness	.02"-.03"
Drawing Number	TF001DGN-WD
Cutting	Scissors

### COLORS



Black (BK)

### CERTIFICATIONS





## ABRASION

Abrasion Resistance	<b>LOW</b>
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	77°F
Humidity	54%
Visible Fraying	100 Test Cycles
Material Destroyed	200 Test Cycles
Pre-Test Weight	8,564.7 mg
Post-Test Weight	6,897.6 mg
Test End Loss Of Mass Point Of Destruction	1,667.1 mg

## FLAMMABILITY

Rating	Flame Resistant
--------	-----------------

## OPERATING TEMPERATURES

Decomposition Temp	842°F / 450°C
Maximum Continuous (Mil-I-23053)	°F / °C
Minimum Continuous	°F / °C

## PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	.01"
Flammability Rating	Flame Resistant
Recommended Cutting	Scissors
Colors	1
Wall Thickness	.02"-.03"
Limited Oxygen Index (LOI)	45-55
Ultraviolet Resistance	Excellent
Char Shrinkage	Excellent
Char Strength	Excellent
Decomposition Temp	842 °F / 450°C

## CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected 4=More Affected 5=Severely Affected

Acid	2
Alkaline	3
Organic Solvent	1
Bleach	4
RoHS	Yes